


S25051 PLASTER FINISHER GREY



1000 ml
1000 ml



Knifing application



24 h at 20°C



0-300µ



24h at 20°C



P 120
P 240

Description

Filler

2K epoxy filler for finishing knifing coats. It has a fine grain and can be used for thin knifing coats aimed at closing porosity of epoxy fillers with light extender and at preparing surfaces for the following painting step.

Colour

Grey

Characteristics

- Good flexibility
- Very good impermeability
- High multipurpose use
- Fast drying

Typical data

Specific weight A and B: 1,54 g/ml
Shore hardness D: 55

Substrate preparation

Stoppani epoxy primers

Dry sanding with P 280-320 paper

Stoppani epoxy fillers

Dry sanding with P 80-120 paper

Application

Knifing.

Application conditions:

- Relative humidity < 80%
- Temperature >10 °C <35°C
- Substrate temperature 5° > dew point

Mixing ratio

		Volume	Weight
S25051	PLASTER FINISHER GREY SOL A	1000 ml	1000 g
S25052	PLASTER FINISHER GREY SOL B	1000 ml	1000 g

Pot life at 20°C: 60'

N° of knifing: 1+1 of refinish, if necessary

Recommended film thickness: up to 300 µ

Theoretical coverage A + B: 3,3 m² for 1lt mixture at 300µ dry film thickness

Rises in temperature causes pot-life reduction.

Drying

	10°C	20°C	35°C
Sanding after	Min. 48 h	Min. 24 h	Min. 12 h

TECHNICAL DATA SHEET N° S198-GB
UPDATED 04/2011

All information here included is the result of carefully controlled tests and expresses our best and up to date knowledge. This news is given only as a guide, so the firm cannot be accountable for further results. Furthermore it cannot be used as a contestation related to the use of the described product. All this is due to the fact that use conditions are not under our control.



Lechler S.p.A. 22100
COMO ITALY - Via Cecilio, 17
Tel. +39.031 586 111 - Fax +39.031 586 206
info@lechler.eu www.lechler.eu